

Old Langford Blend

size 65mm

compressive strength ≥ = 20N/mm²

water absorption ≥ = %15m/md

durability FL / F2

weight per pack 1200kg


pack size 640

active soluble salts content \$2

dry weight per brick 1.8kg

dimensional tolerences T1 Range Category R1

brick type Handmade



call us 01430 432667

email info@crest-bst.co.uk

www. crest-bst.co.uk

visit our showroom
Howdenshire Way
Knedlington Road
Howden
DN14 7H7



