

## Manganese

size 65mm and 50mm

compressive strength 25N/mm<sup>2</sup>

water absorption 14%

**durability** FL / F2

weight per pack 65mm: 1606kg, 50mm: 1500kg

**pack size** 65mm: 730, 50mm: 935

active soluble salts content S2

dry weight per brick 2.20kg / 1.65kg

( EN 771-1 Cat. I - HD

**dimensional tolerences** T1 Range Category R1



**call us** 01430 432667

email info@crest-bst.co.uk

> www. crest-bst.co.uk

visit our showroom Howdenshire Way Knedlington Road Howden DN14 7HZ



